

TEKNISKA DATA

KÄHRS LUXURY TILES

XPRESSION - DRY BACK WOOD OCH STONE



Dry back Xpression Stone
500 x 500 x 2,0 mm





Dry back Xpression Wood
177,8 x 1219,2 x 2,0 mm

PRODUKT













Xpression	EN 14565	PVC- and plasticizer-free Enomer® -Designgolv
Användning	EN ISO 10874	23/34/43



SPECIFIKATION

Tjocklek		EN ISO 24346	2,0 mm
Vikt		EN ISO 23997	3400 g/m ²
Storlek		EN ISO 24342	177,8 x 1219,2 x 2 mm (7" x 48" x 0,08")
Storlek		EN ISO 24342	500 x 500 x 2 mm (20" x 20" x 0,08")

PRODUKTEGENSKAPER

EGENSKAP	TESTMETOD	RESULTAT
Certifieringar för inomhusluft		M1, Floorscore, Österreichisches Ecolabel
Brandklass	 EN 13501-1	C _{fl} -s1
Kvardröjande intrycksmärken	 EN ISO 24343-1	< 0,05 mm
Dimensionsstabilitet	 EN ISO 23999 (50 °C/6 h)	< 0,1 %
Färgbeständighet	 EN ISO 105-B02	≥ 6
Halkmotstånd	 EN 13893 DIN 51130	DS (> 0,3) R9
Elektriska egenskaper	 EN 1815	< 2 kV (antistatisk)
Slitmotstånd	 EN 660-2 ISO 5470-1	< 2,0 mm ³ (Group T) 0,05 g/1000 cykler
Motståndskraft mot kemikalier	 EN ISO 26987	Utmärkt
Termisk resistans	 EN 12664:2001	0,009 m ² K/W
Stolshjulsbelastning	 EN 425	Lämpligt
Golvvärme	 EN 12664:2001	Lämpligt (max. +27 °C)
Bakterietillväxt		Resistent mot bakterietillväxt
Flexibilitet	 EN ISO 24344 Method A	40 mm





TEKNISKA DATA
KÄHRS LUXURY TILES

XPRESSION - DRY BACK WOOD

177,8 x 1219,2 x 2 mm (7" x 48" x 0,08")



1511 Xpression Almond



1504 Xpression Smoked



1512 Xpression Dune



1514 Xpression Chestnut



1503 Xpression Natural




1515 Xpression Charcoal



1513 Xpression Hazel




1501 Xpression Warm Grey



1516 Xpression Golden Oak



1502 Xpression Cool Grey



1519 Xpression American Cherry




1505 Xpression Dark Grey



1517 Xpression French Walnut

XPRESSION - DRY BACK STONE

500 x 500 x 2 mm (20" x 20" x 0,08")




1531 Xpression Light



1542 Xpression Sand



1545 Xpression Slate



1551 Xpression Faded