



TEST REPORT

DATE: 10-25-2017

Page 1 of 2

TEST NUMBER: 0241320

| | |
|---------------|----------|
| CLIENT | UPOFLOOR |
|---------------|----------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM F2055 Test Method for Size and Squareness of Resilient Floor Tile by Dial Gage Method |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|----------------------|
| IDENTIFICATION | Zero Tiles 5112/9501 |
| LOT NUMBER | 25617 |
| CONSTRUCTION | Vinyl Tile |

GENERAL PRINCIPLE

This test method covers the determination of both dimensions (length and width) and squareness of resilient floor tile. The gage dials were set at the listed specified size and reported as deviation from the 24 inch zero point. Results are listed in inches.

TEST RESULTS

| Specified Size in Inches | |
|--------------------------|--------|
| Length | Width |
| 19.685 | 19.685 |

| #1 | Gage A | Gage B | Gage C | Squareness Gage D |
|--------------------|--------|--------|----------------------|-------------------|
| Side 1 | -0.008 | -0.012 | -0.011 | 0.032 |
| Side 2 | -0.014 | -0.013 | -0.015 | 0.031 |
| Side 3 | -0.011 | -0.012 | -0.008 | 0.026 |
| Side 4 | -0.015 | -0.013 | -0.014 | 0.029 |
| | | | Per Linear Ft | |
| Length Deviation L | | -0.008 | -0.005 | |
| Length Deviation C | | -0.012 | -0.007 | |
| Length Deviation R | | -0.011 | -0.007 | |
| Width Deviation L | | -0.014 | -0.009 | |
| Width Deviation C | | -0.013 | -0.008 | |
| Width Deviation R | | -0.015 | -0.009 | |

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.



TEST REPORT

DATE: 10-25-2017

Page 2 of 2

TEST NUMBER: 0241320

| | |
|---------------|----------|
| CLIENT | UPOFLOOR |
|---------------|----------|

| | |
|------------------------------|--|
| TEST METHOD CONDUCTED | ASTM F2055 Test Method for Size and Squareness of Resilient Floor Tile by Dial Gage Method |
|------------------------------|--|



| DESCRIPTION OF TEST SAMPLE | |
|----------------------------|----------------------|
| IDENTIFICATION | Zero Tiles 5112/9501 |
| LOT NUMBER | 25617 |
| CONSTRUCTION | Vinyl Tile |

| #2 | Gage A | Gage B | Gage C | Squareness Gage D |
|--------------------|--------|--------|----------------------|-------------------|
| Side 1 | -0.015 | -0.017 | -0.017 | 0.032 |
| Side 2 | -0.015 | -0.018 | -0.022 | 0.033 |
| Side 3 | -0.017 | -0.017 | -0.015 | 0.030 |
| Side 4 | -0.022 | -0.018 | -0.015 | 0.030 |
| | | | Per Linear Ft | |
| Length Deviation L | | -0.015 | -0.009 | |
| Length Deviation C | | -0.017 | -0.010 | |
| Length Deviation R | | -0.017 | -0.010 | |
| Width Deviation L | | -0.015 | -0.009 | |
| Width Deviation C | | -0.018 | -0.011 | |
| Width Deviation R | | -0.022 | -0.013 | |

| #3 | Gage A | Gage B | Gage C | Squareness Gage D |
|--------------------|--------|--------|----------------------|-------------------|
| Side 1 | -0.006 | -0.008 | -0.010 | 0.039 |
| Side 2 | -0.014 | -0.013 | -0.016 | 0.030 |
| Side 3 | -0.010 | -0.008 | -0.006 | 0.032 |
| Side 4 | -0.016 | -0.013 | -0.014 | 0.032 |
| | | | Per Linear Ft | |
| Length Deviation L | | -0.006 | -0.004 | |
| Length Deviation C | | -0.008 | -0.005 | |
| Length Deviation R | | -0.010 | -0.006 | |
| Width Deviation L | | -0.014 | -0.009 | |
| Width Deviation C | | -0.013 | -0.008 | |
| Width Deviation R | | -0.016 | -0.010 | |

APPROVED BY: *Gary Anthony*

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.