



TFI Report 471376-02

Classification

of the Reaction to Fire according to EN 13501-1:2010

Customer

Upofloor Oy
Souranderintie 2
37101 Nokia
FINLAND

Product

resilient floor covering
Zero Tile
Product ID tested: Zero Tile 5123, batch 9470

This report includes 4 pages and 0 annex(es).

Responsible at TFI

Dipl.-Ing. Ulrike Balg
senior engineer fire testing
Tel: +49 241 9679 133
u.balg@tfi-aachen.de

Aachen, 25 September 2017




Dr. Alexander Siebel
head of the testing laboratory

The present document is provided with an advanced electronic signature.

This report only applies to the tested samples and has been established to the best of our knowledge. Only the entire report shall be reproduced. Under no circumstances, extracts shall be used. Furthermore, we apply the "General Terms and Conditions for the Execution of Contracts" of the TFI Aachen GmbH, also with regard to the order execution.



Notified Body
No. 1658



Testing laboratory,
inspection and certification
body recognised by the DIBt
(Deutsches Institut für Bautechnik)



Accredited for the methods indicated
in the annex to the DAkkS certificate

TFI Aachen GmbH
Charlottenburger Allee 41
52068 Aachen · Germany
www.tfi-aachen.de

HRB 8157 Aachen
VAT No. DE209411312
Managing Director
Univ.-Prof. Prof. h.c. (MGU)
Dr.-Ing. Dipl.-Wirt.-Ing.
Thomas Gries

1 Transaction

Test order	Classification of the reaction to fire according to EN 13501-1:2010
Order date	23 August 2017
Your reference	S. Löytönen
Product designation(s)	Zero Tile Product ID tested: Zero Tile 5123, batch 9470
TFI sample number	17-08-0176

2 Product specification

The construction product is completely described in the test report mentioned under item 3. The test report provides the basis for the present classification.

3 Results

3.1 Test reports and test results used for the classification

Test laboratory	Customer	Test report no.	Test method
TFI Aachen GmbH	Upofloor Oy	471376-01 dated 25 September 2017	EN ISO 9239-1:2010
			EN ISO 11925-2:2010 (15 s ignition time)

3.2 Test results

	Test method	Parameter	Number of tests	Result	
				Mean value	Requirements fulfilled (Y/N)
Product	EN ISO 9239-1:2010	Average critical heat flux [kW/m ²]	3	9.8	
		Integrated smoke value [% x min.]		30	
	EN ISO 11925-2:2010	Flame tip < 150 mm	6	-	Y

3.3 Classification and field of application

The construction product "Zero Tile Product ID tested: Zero Tile 5123, batch 9470" is classified as follows with regard to the reaction to fire:

B_{fl}

The additional classification with regard to the smoke development is:

s1

The additional classification with regard to burning droplets/particles is:

-

The format of the reaction to fire classification for floor coverings is:

Reaction to fire		Smoke development	
B_{fl}	-	s	1

Classification of the reaction to fire: B_{fl} - s1



This classification is valid for the following end use application:

Type of end use application	horizontally laid floor covering
Substrate	noncombustible substrates (Euroclass A1 and A2-s1,d0) with a gross density $\geq 1350 \text{ kg/m}^3$
Underlay for installation	no
Type of fixation	glued
Adhesive	glued with UZIN KE 2000 S, Uzin Utz AG (or adhesives which ensure that the tested construction product will reach at least the same fire class)
Joint according to EN ISO 9239-1:2010	yes

Limitations

This classification document does not represent any type approval or certification of the product.

The classification assigned to the construction product in this report is suited for a declaration of conformity by the manufacturer or a Declaration of Performance within the context of system 3 attestation of conformity and CE marking under the Construction Products Directive or Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This declaration confirms that the design of the product does not require any specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic contents or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence, the manufacturer has concluded that system 3 for the attestation of conformity respectively system 3 for the assessment and verification of the constancy of performance is appropriate

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.