

TECHNICAL DATA

ZERO & GREEN

ENOMER® CONTRACT SHEET FLOORING

PRODUCT

Zero Sheet	EN 14565	PVC- and plasticizer-free Enomer® flooring
Application	EN ISO 10874	23/34/43



SPECIFICATION


Thickness	EN ISO 24346	~0.08" (2.0 mm)
Weight	EN ISO 23997	~0.64 lbs / sq ft (3100 g/m²)
Roll length	EN ISO 24341	82.02' (10 - 25 m)
Width	EN ISO 24341	4'9" (145 cm)

PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Electrostatic Propensity	AATCC 134	< 2.0 kV
Electrical Resistance	ASTM F 150	> 50 GΩ
Slip Resistance DCOF (Wet)	ANSI B 101.3	Acceptable
Static Coefficient of Friction	ASTM C 1028	Pass
Abrasion Resistance w weight loss	ASTM D 4060	0.05 g/1000 cycles
Castor Chair Test 25.000 cycles	EN 425	Pass
Critical Radiant Flux	ASTM E 648	≥ 0.45 W/cm² Class 1
Smoke Density	ASTM E 662	≤ 450 Flaming & Non-flaming
Flexibility	ASTM F 137	Pass (8 mm mandrel)
Resistance to Heat	ASTM F 1514	Pass
Resistance to Light	ASTM F 1515	Pass
Short Term Indentation	ASTM F 1914	0.003" at 75 lbs
Chemical Resistance	ASTM F 925	Excellence
Static Load Limit	ASTM F 970	0.001"
Static Load Limit	ASTM F 970 Mod	2000 psi
Resistance to bacteria and fungi	ISO 846	Good

Kährs

COLLECTION
ZERO & GREEN
ENOMER® CONTRACT SHEET FLOORING




5311 SILVER GREY




5312 CONCRETE



5302 CAPE COD



5303 PEWTER




5304 STONE GREY




5322 DUSTY



5364 AMBROSIA



5352 BLUE MOON



5323 MOROCCO



5329 SUNBEAM